



FLEX-GARD[®]

2K METAL WRAP

7.4 lbs/3000ft² (12 g/m²) white PE coating
5X3 PE woven

7.4 lbs/3000ft² (12 g/m²) white PE laminant
40.0 lbs/3000ft² (65 g/m²) natural kraft

*available with volatile corrosion inhibitor

Product Performance		
Physical Characteristics		Test Method
Basis Weight	: 84.4 lbs/3000ft ² : (137.4 g/m ²)	<i>Tappi</i> <i>T-410 om-02</i>
Grab Tensile Strength	: MD 98.1 lbs/in (44.5 kg/in) : CD 65.0 lbs/in (29.5 kg/in)	<i>ASTM</i> <i>D5034-95(2001)</i>
Elongation at Max load	: MD 10.2 % : CD 7.7 %	<i>ASTM</i> <i>D5034-95(2001)</i>
Trapezoidal Tear Strength	: MD 38.6 lbs (17.5 kg) : CD 22.0 lbs (10.0 kg)	<i>ASTM</i> <i>D5587-03</i>
Tongue Tear	: MD 13.7 lbs (6.2 kg) : CD 15.7 lbs (7.1 kg)	<i>ASTM</i> <i>D2261-96(2002)</i>
Beach Puncture	: 11.9J	<i>Tappi</i> <i>T-803-99</i>
Mullen Burst	: 118 psi (814 kPa)	<i>ASTM</i> <i>D3786-01</i>

Results above are typical properties for the product. They do not constitute a limiting specification for the product.